

- ▶ Butyl rubber is a product of copolymerization of isobutylene and isoprene.
- ▶ Product characteristics: density 0,92 g/cm³; appearance- bale from white to light beige color; weight of a bale 30±1 kg.
- ▶ Shelf life is two (2) years since the date of manufacture. Storage conditions: at the temperature not higher than 40 °C, in place protected from direct sunlight and atmospheric precipitation.
- ▶ Packing: polyethylene film with a thickness of 0,06 – 0,07 mm, Vicat softening temperature ≤ 95 °C;
Package: metal container MB-5 1,26 mt, plywood 1,26 mt or plastic 0,54 mt.

Parameter	IIR-1675	IIR-1675 grade M	Test method
Mooney viscosity UML 1+8 (125 °C)	46-56	35-47	ASTM D 1646
Unsaturation, mol %	1,4 - 1,8		method of supplier
Volatile matter content, wt %	max. 0,3	Max. 0,4	ASTM D 5668
Non-staining Antioxidant content, wt % (CAS № 6683-19-8)	0,02-0,08		method of supplier
Ash content, wt %	max.0,3	max. 0,3	ASTM D 5667